

会社名：三昌フォームテック(株)

JEPSA EPS建材推進委員会
熱抵抗値(単位: m²・K/W)
小数点以下2位四捨五入

製品名	YSKボード1号	YSKボード2号	YSKボード3号	YSKボード4号
JIS又はEI認証	EI(SF14B001)	EI(SF14B001)	EI(SF14B001)	EI(SF14B001)
熱伝導率 (W/m・K)	0.034	0.035	0.036	0.038
厚み(mm) ↓	－	－	－	－
40	1.2	1.1	1.1	1.1
45	1.3	1.3	1.3	1.2
50	1.5	1.4	1.4	1.3
55	1.6	1.6	1.5	1.4
60	1.8	1.7	1.7	1.6
65	1.9	1.9	1.8	1.7
70	2.1	2.0	1.9	1.8
75	2.2	2.1	2.1	2.0
80	2.4	2.3	2.2	2.1
85	2.5	2.4	2.4	2.2
90	2.6	2.6	2.5	2.4
95	2.8	2.7	2.6	2.5
105	3.1	3.0	2.9	2.8
110	3.2	3.1	3.1	2.9
115	3.4	3.3	3.2	3.0
120	3.5	3.4	3.3	3.2
125	3.7	3.6	3.5	3.3
130	3.8	3.7	3.6	3.4
140	4.1	4.0	3.9	3.7
150	4.4	4.3	4.2	3.9
160	4.7	4.6	4.4	4.2
165	4.9	4.7	4.6	4.3
175	5.1	5.0	4.9	4.6
180	5.3	5.1	5.0	4.7
185	5.4	5.3	5.1	4.9
195	5.7	5.6	5.4	5.1
200	5.9	5.7	5.6	5.3
210	6.2	6.0	5.8	5.5
235	6.9	6.7	6.5	6.2
240	7.1	6.9	6.7	6.3
250	7.4	7.1	6.9	6.6
265	7.8	7.6	7.4	7.0
275	8.1	7.9	7.6	7.2
280	8.2	8.0	7.8	7.4
285	8.4	8.1	7.9	7.5
300	8.8	8.6	8.3	7.9
350	10.3	10.0	9.7	9.2
400	11.8	11.4	11.1	10.5